

## ORANGE LABEL



**100 %**  
Recycled



**70**  
ISO



**80**  
gsm

Saveco Orange Label office paper is made from 100% recycled fibre in an integrated, energy-efficient and resource-friendly process that is entirely chlorine free. This high-performance multi-purpose paper has excellent eco credentials, including Blue Angel and FSC Recycled® certification. Ideal for all types of corporate communications, it comes in a wide range of sizes and weights. It also offers excellent runnability and processing as per **DIN EN 12281**.



### Technical data

<b>Grammage</b>	ISO 536		g/m <sup>2</sup>	<b>80 ± 3,2</b>
<b>Thickness</b>	ISO 534		µm	<b>102 ± 6,0</b>
<b>ISO brightness</b>	ISO 2470		%	<b>70 ± 2,5</b>
<b>CIE whiteness</b>	ISO 11475		%	<b>65 ± 2,5</b>
<b>Opacity</b>	ISO 2471		%	<b>&gt; 95</b>
<b>Bendtsen roughness</b>	ISO 8791-2		ml/min.	<b>260 ± 160</b>

### Certification



[www.blauer-engel.de/uz14a](http://www.blauer-engel.de/uz14a)



### Runnability/ resistance to ageing



Product complies with DIN EN 12281; resistant to ageing as per ISO 20494.

---

## Product description

Raw material  
Filler  
Surface  
Sizing  
Auxiliary material

## Multifunctional office paper for laser and inkjet printers

wood pulp-containing and wood-free press waste paper from printing companies and collections, according to the regulations of the Blue Angel (DE-UZ 14a)  
kaolin and calcium carbonate  
starch treated  
neutral sizing with synthetic sizing agents  
the auxiliary material used are free from organic chlorine compounds and do not lead to the formation of AOX

---

## Application areas

photocopiers, side printer (LED, laser, magnet, ions),  
inkjet printer, fax, pre-printing

---

## Assortment

80, 90, 100 and 120 g/gsm  
A4, A3, SR A3 and reels,  
as well as punched, double and 4 times punched  
Further products on request

---

## Manufacturer

Saveco GmbH  
Stollberger Str. 53,  
09399 Niederwürschnitz – Germany

---

## Certifications of the manufacturer



---

## Storage conditions

optimal room temperature min. 10 °C max. 30 °C  
Relative humidity min. 30% RH max. 70% RH  
Close opened package again when not in use

---

## Processing recommendation

Allow the paper to adapt to the room climate 24 hours before use.  
Best runability between 18 °C and 24 °C temperature and between 40% RH and 60% RH relative humidity

---

## Recycling

This product can be 100% recycled after use.

---